



TIBCHEMICALS

PROTEGOL® EP Coating 32-89 S-L two-component epoxy coating

Description

PROTEGOL® EP Coating 32-89 S-L is a two-component epoxy coating. The product meets the requirements of DIN EN 10289, 02.2002. Application is made by Spatula, knife.

Uses

Internal and external coating of

- Pipes, pipe bends
- Fittings
- Tanks, containers

Benefits

- Excellent corrosion protection
- Good adhesion to steel
- Abrasion-resistant and impact-resistant
- Good chemical resistance

Product data

The following data has been obtained at +23°C unless otherwise stated:

Type	epoxide
Component A (Base)	epoxide
Component B (Hardener)	amine
Physical state	
Component A	viscous
Component B	pasty
Viscosity	
Comp. A at 25 °C	6700 mPa*s
Comp. B at 25 °C	5000 mPa*s
Density (g/cm ³)	
Comp. A	1,52
Comp. B	1,39
Comp. A + B	1,47
Mixing ratio Comp A : Comp B	
Gravimetric	69:31
Volumetric	2,0:1,0

Coating properties

Recommended dry film thickness ≥1500 µm

Actual required DFT may vary in certain applications, please contact us for technical

clarification.

Service temperature	-20 °C to 100 °C
Minimum surface temperature	10 °C
min. +3°C above dew point	
Processing temperature	
Component A	15 °C to 25 °C
Component B	15 °C to 25 °C

Max. rel air humidity 80 %

Potlife at 25 °C 25 min

Coating properties according to DIN EN 10290:2002/10289:2002 (typical values)

Hardness Shore D (±5) 85

Impact resistance (max. impact energy) 5 J/mm

Coating properties according to other standards (typical values)

Adhesion to FBE (internal test) 20,4 MPa

Adhesion to FBE (28-day hot water soak; internal test) 20,5 MPa (80° C)

Colours

Other colors on request (subject to technical feasibility and minimum order quantities)

Coverage, theoretical

Approx. 1,47 kg/m² at 1.000 µm DFT and not considering excess consumption.

Packing

Component A	Component B
tin 1,38 kg	tin 0,62 kg

Shipping and Storage Regulations, Application, Health and Safety

Storage:

In a cool and dry place shelf life is approx. 24 months in tightly closed original packs.

Maintenance of tools:

Immediately after use, all tools should be cleaned with .

Refer to our general work instructions for

Release 7/7/2023



TIBCHEMICALS

PROTEGOL® EP Coating 32-89 S-L two-component epoxy coating

PROTEGOL® Coatings.

Refer to our safety data sheets prior to use.

Carefully read and follow all safety instructions on labels and packaging. Handle and store material with care in accordance with the safety data sheets. Follow and observe any applicable local or national laws and regulations.

Regulations regarding explosion protection with regard to the construction and equipment of facilities (machines) can be found, among other sources, in the corresponding harmonized European standard (BS EN 16985:2018-12-14 "Spray booths for organic coating material - Safety requirements" (former DIN EN 12215 and DIN EN 13355)); furthermore, local laws and/or regulations must be observed.

Contact us to make sure you have the latest version of safety data sheet, technical data sheet and work instruction at hand.

Important Notice:

The information on the properties of the product components represent average values that correspond to our defined quality specifications. Our products are manufactured and controlled in accordance with strict quality management and quality control requirements, which are subject to ISO 9001: 2015 certification. Information on the default values defined by us are given in the acceptance test certificates. The product properties marked as "typical values" are taken from the test reports of external institutes, unless otherwise stated. The information in our documents in printed or electronic form is based on our knowledge and experience. Due to numerous possible influences in the processing and application of our products, our statements do not release the processor from the responsibility to test the goods for their own procedures and purposes; Legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information. It is the responsibility of the recipient of our products to observe any property rights as well as existing laws and regulations.

Release 7/7/2023

