



# TIBCHEMICALS

## PROTEGOL® PU Repair two-component polyurethane coating

### Description

PROTEGOL® PU Repair is a two-component polyurethane coating. The product meets the requirements of DIN EN 10290:2002.

Application is made by mechanical operating dispenser.

The product can also be used to repair factory and field coatings

### Uses

Internal and external coating of

- Pipes, pipe bends
- Fittings
- Field joints
- Metal surfaces prone to corrosion
- Bonding of anodes in cathodic corrosion protection

### Benefits

- Very fast reaction and curing time
- Easy to use
- No waste of material
- Excellent corrosion protection

### Referenced Standards

**DIN EN 10290:2002** Steel tubes and fittings for onshore and offshore pipelines - External liquid applied polyurethane and polyurethane-modified coatings

### Product data

The following data has been obtained at +23°C unless otherwise stated:

Type	polyurethane
Component A (Base)	polyol
Component B (Hardener)	isocyanate

Physical state	
Component A	viscous
Component B	liquid

Viscosity	
Comp. A at 25 °C	5500 mPa*s
Comp. B at 25 °C	4000 mPa*s

Density (g/cm <sup>3</sup> )	
Comp. A	1,24
Comp. B	1,24
Comp. A + B	1,24

Mixing ratio Comp A : Comp B	
Gravimetric	50:50
Volumetric	1,0:1,0

### Coating properties

Recommended dry film thickness	≥1500 µm
Actual required DFT may vary in certain applications, please contact us for technical clarification.	

Service temperature	-20 °C to 80 °C
Short term temperature load without temperature gradient to the substrate	110 °C
Minimum surface temperature	5 °C
min. +3°C above dew point	
Processing temperature	
Component A	15 °C to 35 °C
Component B	15 °C to 35 °C

Max. rel air humidity	80 %
-----------------------	------

Potlife at 23 °C	60 sec
------------------	--------

### Coating properties according to DIN EN 10290:2002/10289:2002 (typical values)

Hardness Shore D (±5)	75
according DIN EN ISO 686 (1 sec.)	

Impact resistance (max. impact energy)	14 J/mm
Adhesion to steel	18 MPa

Cathodic disbondment after 28 d at 23 °C	1,00 mm
--	---------

Specific electrical insulation resistance after 100 d at 23 °C	1,7*10 <sup>8</sup> Ωm <sup>2</sup>
--	-------------------------------------

Thermal aging, adhesion ( 100 d)	16 MPa (100° C)
Flexural strength	pass
Elongation at break	17 %

Cleaning agent	Solvent B, G
Repair material	PROTEGOL® PU Repair

### Colours

RAL 9011 - Graphite black

Other colours on request (subject to technical feasibility and minimum order quantities)

Release 7/4/2023



# TIBCHEMICALS

## PROTEGOL® PU Repair two-component polyurethane coating

### Coverage, theoretical

Approx. 1,24 kg/m<sup>2</sup> at 1.000 µm DFT and not considering excess consumption.

*to observe any property rights as well as existing laws and regulations.*

### Packing

Component A	Component B
2K cartridge 0,03 kg	0,03 kg

### Shipping and Storage Regulations, Application, Health and Safety

#### Storage:

In a cool and dry place shelf life is approx. 12 months in tightly closed original packs.

#### Maintenance of tools:

Immediately after use, all tools should be cleaned with Solvent B, G.

Refer to our general work instructions for PROTEGOL® Coatings.

Refer to our safety data sheets prior to use.

Carefully read and follow all safety instructions on labels and packaging. Handle and store material with care in accordance with the safety data sheets. Follow and observe any applicable local or national laws and regulations.

Regulations regarding explosion protection with regard to the construction and equipment of facilities (machines) can be found, among other sources, in the corresponding harmonized European standard (BS EN 16985:2018-12-14 "Spray booths for organic coating material - Safety requirements" (former DIN EN 12215 and DIN EN 13355)); furthermore, local laws and/or regulations must be observed.

Contact us to make sure you have the latest version of safety data sheet, technical data sheet and work instruction at hand.

#### *Important Notice:*

*The information on the properties of the product components represent average values that correspond to our defined quality specifications. Our products are manufactured and controlled in accordance with strict quality management and quality control requirements, which are subject to ISO 9001: 2015 certification. Information on the default values defined by us are given in the acceptance test certificates. The product properties marked as "typical values" are taken from the test reports of external institutes, unless otherwise stated.*

*The information in our documents in printed or electronic form is based on our knowledge and experience. Due to numerous possible influences in the processing and application of our products, our statements do not release the processor from the responsibility to test the goods for their own procedures and purposes; Legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information. It is the responsibility of the recipient of our products*

Release 7/4/2023

TIB Chemicals AG | Mülheimer Straße 16 -22 | 68219 Mannheim | Postfach 81 02 20 | 68202 Mannheim  
Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

