



TIBCHEMICALS

PROTEGOL® UR Coating 32-45/55 L solvent-free two-component polyurethane coating

Description

PROTEGOL® UR Coating 32-45/55 L is a two-component polyurethane coating. The product meets the requirements of DIN EN 10290:2002. Application is made by Spatula, knife or Brush. The product is a complementary product to PROTEGOL® UR Coatings for manual processing.

Uses

Coating of

- Field joints
- Pipes, pipe bends
- Fittings
- Tanks, containers
- Repair of coating imperfections
- Stripe coating of parts of complex shape-environment

Benefits

- Excellent corrosion protection
- Abrasion resistant
- Impact resistant
- Good chemical resistance

Referenced Standards

DIN EN 10290:2002 Steel pipes and fittings for onshore and offshore pipelines - Coating (external coating) with polyurethane and polyurethane-modified materials

Product data

The following data has been obtained at +23°C unless otherwise stated:

Type	polyurethane
Component A (Base)	polyol
Component B (Hardener)	isocyanate

Physical state	
Component A	viscous
Component B	liquid

Viscosity	
Comp. A at 25 °C	16300 mPa*s
Comp. B at 25 °C	200 mPa*s

Density (g/cm ³)	
Comp. A	1,50
Comp. B	1,24
Comp. A + B	1,44

Mixing ratio Comp A : Comp B	
Gravimetric	78,5:21,5
Volumetric	3,0:1,0

Coating properties

Recommended dry film thickness	≥1500 µm
--------------------------------	----------

Actual required DFT may vary in certain applications, please contact us for technical clarification.

Service temperature	-20 °C to 80 °C
Short term temperature load without temperature gradient to the substrate	110 °C
Minimum surface temperature min. +3°C above dew point	10 °C
Processing temperature	
Component A	15 °C to 25 °C
Component B	15 °C to 25 °C

Max. rel air humidity	80 %
-----------------------	------

Potlife at 23 °C	20 min
------------------	--------

Coating properties according to DIN EN 10290:2002/10289:2002 (typical values)

Hardness Shore D (±5)	75
-----------------------	----

Release 8/11/2023



TIBCHEMICALS

PROTEGOL® UR Coating 32-45/55 L solvent-free two-component polyurethane coating

Impact resistance (max. impact energy) 5 J/mm
Adhesion to steel 16 MPa

Cathodic disbondment after 28 d
at 23 °C 3,30 mm

Specific electrical insulation resistance
after 100 d at 23 °C $>10^7 \Omega\text{m}^2$

Thermal aging, adhesion (100 d) (80° C)
Flexural strength pass
Elongation at break 12 %

Coating properties according to AWWA (typical values)

Coating properties according to ISO 21809-3 (typical values)

Adhesion (ISO 4624, 23°C)

Adhesion after 28-d hot-water immersion at T_{max}
(Annex I plus ISO 4624)

Ωm^2

Coating properties according to DIN 3476-2 (typical values)

Ωm^2

Ωm^2

Coating properties according to other standards (typical values)

Cleaning agent Solvent B, G
PROTEGOL® PU Repair,
PROTEGOL® UR Coating 32-45/55 L (Cartridge),
PROTEGOL® UR Coating 32-60 (Cartridge)

Colours

RAL 9011 - Graphite black

RAL 5005 - Signal blue

RAL shades are approximate and may vary slightly

Other colors on request (subject to technical feasibility and minimum order quantities)

Coverage, theoretical

Approx. 1,44 kg/m² at 1.000 µm DFT and not considering excess consumption.

Packing

Component A	Component B
tin 1,57 kg	tin 0,43 kg

Shipping and Storage Regulations, Application, Health and Safety

Storage:

In a cool and dry place shelf life is approx. 24 months in tightly closed original packs.

Maintenance of tools:

Immediately after use, all tools should be cleaned with Solvent B, G.

Solvent-free: The product does not contain any volatile organic ingredients (VOC) according to regulation 814.018 (VOCV) of Switzerland (Verordnung 814.018 über die Lenkungsabgabe auf flüchtigen organischen Verbindungen (VOCV)) Refer to our general work instructions for PROTEGOL® Coatings.

Refer to our safety data sheets prior to use.

Carefully read and follow all safety instructions on labels and packaging. Handle and store material with care in accordance with the safety data sheets. Follow and observe any applicable local or national laws and regulations.

Regulations regarding explosion protection with regard to the construction and equipment of facilities (machines) can be found, among other sources, in the corresponding harmonized European standard (BS EN 16985:2018-12-14 "Spray booths for organic coating material - Safety requirements" (former DIN EN 12215 and DIN EN 13355)); furthermore, local laws and/or regulations must be observed.

Contact us to make sure you have the latest version of safety data sheet, technical data sheet and work instruction at hand.

Important Notice:

The information on the properties of the product components represent average

Release 8/11/2023



TIBCHEMICALS

PROTEGOL® UR Coating 32-45/55 L solvent-free two-component polyurethane coating

values that correspond to our defined quality specifications. Our products are manufactured and controlled in accordance with strict quality management and quality control requirements, which are subject to ISO 9001: 2015 certification. Information on the default values defined by us are given in the acceptance test certificates. The product properties marked as "typical values" are taken from the test reports of external institutes, unless otherwise stated.

The information in our documents in printed or electronic form is based on our knowledge and experience. Due to numerous possible influences in the processing and application of our products, our statements do not release the processor from the responsibility to test the goods for their own procedures and purposes; Legally binding assurance of certain properties or suitability for a specific application cannot be derived from our information. It is the responsibility of the recipient of our products to observe any property rights as well as existing laws and regulations.

Release 8/11/2023

TIB Chemicals AG | Mülheimer Straße 16 -22 | 68219 Mannheim | Postfach 81 02 20 | 68202 Mannheim
Telefon +49 621 8901-812 | Fax +49 621 8901-902 | info.protegol@tib-chemicals.com | www.tib-chemicals.com

*This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give.
This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.*

